### § 28.38

the Classing Office, shall have been exposed for such length of time as in the judgment of the Area Director shall be sufficient to put them in proper condition for the purpose.

[52 FR 30882, Aug. 18, 1987]

# § 28.38 Lower grade (of two samples) to determine classification.

If a sample drawn from one portion of a bale is lower in grade or shorter in length than one drawn from another portion of such bale, except as otherwise provided in this subpart, the classification of the bale shall be that of the sample showing the lower grade or shorter length.

#### § 28.39 Cotton reduced in grade.

If cotton be reduced in grade, by reason of the presence of extraneous matter or other irregularities or defects, below its grade according to the official cotton standards of the United States, the grade from which it is so reduced, the grade to which it is so reduced, and the condition or reason which so reduces its grade shall be determined and stated.

[25 FR 5872, June 25, 1960]

## § 28.40 Terms defined; cotton classification.

For the purposes of classification of any cotton or of its comparison with a type or other samples, the following terms shall be construed, respectively, to mean:

- (a) Cotton of perished staple. Cotton that has had the strength of fiber, as ordinarily found in cotton, destroyed or unduly reduced through exposure to the weather either before picking or after baling, or through heating by fire, or on account of water packing, or by other causes.
- (b) Micronaire (mike) reading. The measurement of the fiber fineness and maturity, in combination, of cotton as determined by an airflow instrument. For any cotton that has a micronaire reading of 2.6 or lower, the Classing Office will enter the micronaire reading on all classification memoranda issued for such cotton.
- (c) Gin-cut cotton. Cotton that shows damage in ginning through cutting by

the saws, to an extent that reduces its value more than two grades.

- (d) Reginned cotton. Cotton that has passed through the ginning process more than once, and cotton that, after having been ginned, has been subjected to a cleaning process and then baled.
- (e) Repacked cotton. Cotton that is composed of factors', brokers', or other samples, or of loose or miscellaneous lots collected and rebaled, or cotton in a bale which is composed of cotton from two or more smaller bales or parts of bales that are combined after the cotton leaves the gin.
- (f) False packed cotton. Cotton in a bale (1) containing substances entirely foreign to cotton; (2) containing damaged cotton in the interior with or without any indication of such damage upon the exterior; (3) composed of good cotton upon the exterior and decidedly inferior cotton in the interior, in such manner as not to be detected by customary examination; or (4) containing pickings or linters worked into the bale.
- (g) Mixed packed cotton. Cotton in a bale which, in the sample taken therefrom, shows (1) a difference of three or more grades, or (2) a difference of three or more color groups, or (3) a difference in length of staple of one-eighth inch or more. For purposes of this paragraph, White Cotton (including the Plus grades), Light Gray Cotton, and Gray Cotton shall constitute one color group, and Light Spotted Cotton, Spotted Cotton, Tinged Cotton, and Yellow Stained Cotton shall each constitute a color group.
- (h) Water-packed cotton. Cotton in a bale that has been penetrated by water during the baling process, causing damage to the fiber, or a bale that through exposure to the weather or by other means, while apparently dry on the exterior, has been damaged by water in the interior.

[22 FR 10933, Dec. 28, 1957, as amended at 26
FR 5945, July 1, 1961; 32 FR 7011, May 9, 1967;
52 FR 30882, Aug. 18, 1987]

SAMPLE OR TYPE COMPARISON

### § 28.45 Scope of comparison; requests.

A comparison of cotton samples with a type may be requested with respect to grade, or to staple, including any of